



TÜRKAK TÜRK AKREDİTASYON KURUMU

TURKISH ACCREDITATION AGENCY
tarafından akredite edilmiştir



EFFECTIS ERA AVRASYA TEST VE BELGELENDİRME A.Ş.

TOSB TAYSAD Organize San. Böl. 1. CD. ,15. Yol No: 1

Şekerpinar – Çayırova, KOCAELİ

DENEY RAPORU

TEST REPORT

AB-0556-T

21.09.2015

RFTR15109

Müşterinin adı/adresi Customer name/address	:	NEVPANEL YAPI MADEN ÜRETİM İTH. İHR. SAN. VE TİC. LTD. ŞTİ. Bağdat Cad. Çolakoğlu İş Merkezi No:458/30 Maltepe, İSTANBUL /TURKEY
İstek numarası Order No.	:	EEA-15-000511
Numunenin adı ve tarifi Name and identity of test sample	:	Partition Wall System Consisting of Single Layer of MgO Panels – “NevPanel, DragonBoardTürkiye, MagnumBoard”
Numunenin kabul tarihi The date of receipt of sample	:	06.08.2015
Açıklamalar Remarks	:	
Deneyin yapıldığı tarih Date of test	:	07.08.2015
Raporun sayfa sayısı Number of pages of the Report	:	11 (23 pages including annexes)

Türk Akreditasyon Kurumu(TÜRKAK) deney raporlarının tanınması konusunda Avrupa Akreditasyon Birliği(EA) ve Uluslararası Laboratuvar Akreditasyon Birliği(ILAC) ile karşılıklı tanınma antlaşmasını imzalamıştır.

The Turkish Accreditation Agency(TURKAK) is signatory to the multilateral agreements of the European co-operation for the Accreditation(EA) and of the International Laboratory Accreditation(ILAC) for the Mutual recognition of test reports

Deney ve /veya ölçüm sonuçları, genişletilmiş ölçüm belirsizlikleri (olması halinde) ve deney metotları bu sertifikanın tamamlayıcı kısmı olan takip eden sayfalarda verilmiştir.

The test and/or measurement results, the uncertainties (if applicable) with confidence probability and test methods are given on the following pages which are part of this report



Tarih
Date

21.09.2015

Deney Sorumlusu
Person in charge of test



Burak ACİCBE

Laboratuvar Müdürü
Head of Testing Laboratory



Onur DAĞ

Bu rapor, laboratuvarın yazılı izni olmadan kısmen kopyalanıp çoğaltılamaz.
İmzasız ve mühürsüz raporlar geçersizdir.

This report shall not be reproduced other than in full except with the permission of the laboratory. Testing reports without signature and seal are not valid

Phone: +902626581662

Fax.: +902626581669

E-mail: info@erayonetim.com
turkey@efectis.com

Web: www.erayonetim.com
www.efectis.com

FR1106/REV00/02 04 2012



EFFECTIS ERA AVRASYA TEST VE BELGELENDİRME A.Ş.

AB-0556-T

21.09.2015

RFTR15109

1. SCOPE

Fire resistance test, in conformity with the general requirements of standards EN1363-1:2012, with substitute or additional methods of standard EN 1363-2:1999 and with the particular requirements of standard EN 1364-1:1999 "Fire resistance tests for non-loadbearing elements- Part 1:Walls".

2. TEST LABORATORY

Name : Efectis Era Avrasya Test ve Belgelendirme A.S.
Address : TOSB TAYSAD Organize San. Böl. 1. CD. ,15. Yol No: 1
Şekerpınar – Çayırova, KOCAELİ, TURKEY

3. DESCRIPTION OF THE TEST SPECIMEN

3.1. General

Product identification: Partition Wall System Consisting of Single Layer of MgO Panels – "**NevPanel, DragonBoardTürkiye, MagnumBoard**"

Manufacturer : NEVPANEL YAPI MADEN ÜRETİM İTH. İHR. SAN. VE TİC. LTD. ŞTİ.
Eskişehir Organize Sanayi Bölgesi 28. Cadde No:8 ESKİŞEHİR/TURKEY

Sponsor of test : NEVPANEL YAPI MADEN ÜRETİM İTH. İHR. SAN. VE TİC. LTD. ŞTİ.
Bağdat Cad. Çolakoğlu İş Merkezi No:458/30 Maltepe, İSTANBUL/TURKEY

3.2. Construction

Partition Wall System Consisting of Single Layers of MgO Panels – "**NevPanel, DragonBoardTürkiye, MagnumBoard**" was constructed from vertically positioned boards mounted on a metal stud frame. The total thickness of the partition wall was 93 mm.

One vertical edge was mounted as in practise and the other vertical edge was constructed as a free edge to simulate a wider wall construction in practise.

Bu rapor, laboratuvarın yazılı izni olmadan kısmen kopyalanıp çoğaltılamaz.
İmzasız ve mühürlü raporlar geçersizdir.

This report shall not be reproduced other than in full except with the permission of the laboratory. Testing reports without signature and seal are not valid

Phone: +902626581662

Fax.: +902626581669

E-mail: info@erayonetim.com
turkey@efectis.comWeb: www.erayonetim.com
www.efectis.com

FR1106/REV00/02.04.2012

Page 2 / 11



3.3. Components

3.3.1. Framework

- Edge and intermediate studs:
 - Type: Wall C profile - galvanized steel.
 - Dimensions: 2985 x 42 x 73 x 0,8 mm (l x d x w x t).
 - Fixing:
 - Type : Galvanized steel – NevPanel screw with dowel
 - Dimensions : 12 x 60 mm (Ø x l)
 - Location : 8 pcs for each edge studs. Ctc. distance was 440 mm.
- The studs had 15 mm gap at top to let the profiles expand freely. Each stud has 400 mm distance to each other.
- Rails:
 - Type: Wall U profile –galvanized steel.
 - Dimensions: 2985 x 28 x 75 x 0,8 mm (l x d x w x t)
 - Fixing:
 - Type : Galvanized steel – NevPanel screw with dowel
 - Dimensions : 12 x 60 mm (Ø x l)
 - Location : 8 pcs for each profile. Ctc. distance was 440 mm.

See Figure 1-3 for details.

3.3.2. Panels

- Type: MgO Panels - NevPanel, DragonBoardTürkiye, MagnumBoard
- Nominal density : 1000 kg/m³
- Nominal thickness : 9 mm
- Dimensions: 1220 x 2440 mm (w x l) - 2 panel at each side next to the free edge
 560 x 2440 mm (w x l) – 1 panel at each side next to the fixed edge
 1220 x 560 mm (w x l) – 2 panel at each side next to the top of the free edge
 560 x 560 mm (w x l) – 1 panel at each side next to the top of the fixed edge

Bu rapor, laboratuvarın yazılı izni olmadan kısmen kopyalanıp çoğaltılamaz.

İmzasız ve mühürsüz raporlar geçersizdir.

This report shall not be reproduced other than in full except with the permission of the laboratory. Testing reports without signature and seal are not valid



Phone: +902626581662

Fax.: +902626581669

E-mail: info@erayonetim.com
turkey@efectis.com

Web: www.erayonetim.com
www.efectis.com

FR1106/REV00/02.04.2012

Page 3 / 11



EFFECTIS ERA AVRASYA TEST VE BELGELENDİRME A.Ş.

AB-0556-T

21.09.2015

RFTR15109

- Fixing:
 - Type: Galvanized steel screw – NevPanel Point head screw
 - Dimensions : 3,9 x 25 mm (\varnothing x l).
 - Locations : Fixed the panel to the steel framework. 9 pcs for each studs. Ctc distance was 300 mm.
- Joints:
 - Type: Water based joint paste – NevPanel N01
 - Dry density : 1556,5 \pm 20 kg/m³
 - Consumption : 150 gr/m²
 - Location : Between the panels.
 - Reinforcement: Joint tape
 - Type : Fibre-glass self-adhesive mesh tape – NevPanel
 - Width : 50 mm
 - Nominal mass per unit area: 46 g/m²
 - Type: Water based finishing paste – NevPanel N01
 - Dry density : 1395,5 \pm 20 kg/m³
 - Consumption : 150 gr/m²
 - Location : On the joint tape surface.

3.3.3. Insulation

- Type : Stone wool – WOOLER
- Nominal thickness : 50 mm
- Density : 50 kg/m³

For further information, see figures 1-3.

Bu rapor, laboratuvarın yazılı izni olmadan kısmen kopyalanıp çoğaltılamaz.
İmzasız ve mühürsüz raporlar geçersizdir.

This report shall not be reproduced other than in full except with the permission of the laboratory. Testing reports without signature and seal are not valid



Phone: +902626581662

Fax.: +902626581669

E-mail: info@erayonetim.com
turkey@efectis.comWeb: www.erayonetim.com
www.efectis.com

FR1106/REV00/02.04.2012

Page 4 / 11



EFFECTIS ERA AVRASYA TEST VE BELGELENDİRME A.Ş.

AB-0556-T

21.09.2015

RFTR15109

4. PRE-TEST PROCESSES

4.1. Verification of specimen

Efectis Era Avrasya A.S. verified the used materials and parts against the supplied data and drawings during installation of the test specimen and not involved in the selection of test specimen.

The test specimen was assembled by the sponsor (NEVPANEL YAPI MADEN ÜRETİM İTH. İHR. SAN. VE TİC. LTD. ŞTİ.)

4.2. Conditioning

The construction was stored in the laboratory of Efectis Era Avrasya A.S. under the following conditions:

- Ambient temperature: $31,8 \pm 1,8$ °C.
- Relative humidity: 58 ± 9 %.

5. TEST PROCESS

5.1. Method

The fire test was conducted according to the standard EN 1364-1:1999.

The heating of the furnace followed the standard fire curve, as specified in the standard EN 1363-1:2012.

The target overpressure in the furnace was 0 Pa at 500 mm above floor level and 19 Pa at the top of the test specimen.

5.2. Measurements

Following test data were measured during the test:

- Ambient temperatures inside the furnace with six plate thermocouples (Furnace TC1 to TC6), evenly distributed over the directly heated surface (see figure A1).
- The pressure in the furnace, measured at a height of 2,9 meter above the furnace floor level (see figure A3).
- Ambient temperature in the laboratory (see figure A4)
- The surface temperatures on the unexposed side of the test specimen (TC 3 up to TC16, see figure B2 and B3).
- Deflection measurements of the test specimen (see figure B4 and Table B1).
- There was no need to use roving thermocouple.
- The positions of the thermocouple and displacement measurements are given in figure B1.

Bu rapor, laboratuvarın yazılı izni olmadan kısmen kopyalanıp çoğaltılamaz.
İmzasız ve mühürlü raporlar geçersizdir.

This report shall not be reproduced other than in full except with the permission of the laboratory. Testing reports without signature and seal are not valid



Phone: +902626581662

Fax.: +902626581669

E-mail: info@erayonetim.com
turkey@efectis.comWeb: www.erayonetim.com
www.efectis.com

FR1106/REV00/02.04.2012

Page 5 / 11

6. OBSERVATIONS

Table 1: Observations during heating

0	Heating started. See photo C1-C2.
13	Smoke release at edge of the specimen.
29	Deformation at middle panel increased ≈ 10 cm
31	Joint tapes started to remove from the panels.
33	Opening at fixed edge between panels and test frame.
38	Horizontal joint cracked and blackened.
40	Cotton pad was applied to opening zone at fixed edge. No ignition.
46	Temperature increased at Thermocouple Nr. 14, $\Delta T > 180$ °C. Insulation (I) failed.
48	Opening at the horizontal joint. Cotton pad was applied, ignition. Integrity (E) failed.
49	Test was terminated after consulted with the customer. See photo C4-C5.

7. TEST RESULTS

7.1 Results

The results are given in Table 2 and appendixes B and C.

During the heating the temperature in the laboratory complied with the standard EN 1363-1:2012.

7.2 Uncertainty of measurements

Due to the nature of fire resistance testing, in which several non-linear effects are present in both the test configuration and the test specimen, which influence each other, it is at this moment not yet possible to give a stated degree of uncertainty of measurement



Bu rapor, laboratuvarın yazılı izni olmadan kısmen kopyalanıp çoğaltılamaz.

İmzasız ve mühürlü raporlar geçersizdir.

This report shall not be reproduced other than in full except with the permission of the laboratory. Testing reports without signature and seal are not valid

Phone: +902626581662

Fax.: +902626581669

E-mail: info@erayonetim.com
turkey@epectis.com

Web: www.erayonetim.com
www.epectis.com

FR1106/REV00/02.04.2012

Page 6 / 11

8. SUMMARY

The most important results of the examination are given in table 2.

Table 2: Summary of test results of the test specimen

Integrity, (E)	
- Cotton pad	48 th minute.
- Gap gauges \varnothing 6 mm	no failure (not applied)
\varnothing 25 mm	no failure (not applied)
- Flames longer than 10 sec.	not observed.
Insulation:, [I]	
- average temperature	48 th minute due to the failure of Integrity
- maximum temperature	46 th minute by TC 14.
The heating was terminated at 49 th minute after consulted with the customer.	

9. FIELD OF DIRECT APPLICATION OF TEST RESULTS

9.1 General

This report details the method of construction, the test conditions and the results obtained when the specific elements of construction described herein was tested following the procedure outlined in EN 1363-1:2012, and when appropriate EN 1363-2:1999. Any significant deviation with respect to size, constructional details, load stresses, edge or end conditions other than those allowed under the field of direct application in the relevant test method is not covered by this report

9.2 Specific conditions for dimensions and fixing

- decrease in height
- increase in wall thickness
- increase in thickness of materials
- reduction in linear dimensions of panels, but not thickness
- reduction of stud spacing
- reduction of fastening point spacing
- increase in the number of horizontal joints

Bu rapor, laboratuvarın yazılı izni olmadan kısmen kopyalanıp çoğaltılamaz.
İmzasız ve mühürsüz raporlar geçersizdir.

This report shall not be reproduced other than in full except with the permission of the laboratory. Testing reports without signature and seal are not valid

Phone: +902626581662

Fax.: +902626581669

E-mail: info@erayonetim.com
turkey@efectis.com

Web: www.erayonetim.com
www.efectis.com

FR1106/REV00/02.04.2012

Page 7 / 11





EFECTIS ERA AVRASYA TEST VE BELGELENDİRME A.Ş.

AB-0556-T

21.09.2015

RFTR15109

9.3 Extension of height

The height of the construction may be increased to 4 meters for a fire resistance of **20 minutes** for the criteria integrity and thermal insulation, because the lateral deflection of the construction is less than 100 mm. See Table B1 – Appendix B.

9.4 Extension of width

The width of an identical construction may be increased, because the construction is tested with a width of 3 meters with one vertical free edge.

Bu rapor, laboratuvarın yazılı izni olmadan kısmen kopyalanıp çoğaltılamaz.
İmzasız ve mühürlü raporlar geçersizdir.

This report shall not be reproduced other than in full except with the permission of the laboratory. Testing reports without signature and seal are not valid

Phone: +902626581662

Fax.: +902626581669

E-mail: info@erayonetim.com
turkey@efectis.comWeb: www.erayonetim.com
www.efectis.com

FR1106/REV00/02.04.2012

Page 8 / 11





Figure 2: Details of the materials



Figure 3: Cross section view of the test specimen.

Bu rapor, laboratuvarın yazılı izni olmadan kısmen kopyalanıp çoğaltılamaz.
İmzasız ve mühürsüz raporlar geçersizdir.

This report shall not be reproduced other than in full except with the permission of the laboratory. Testing reports without signature and seal are not valid

Phone: +902626581662

Fax.: +902626581669

E-mail: info@erayonetim.com
turkey@efectis.com

Web: www.erayonetim.com
www.efectis.com

FR1106/REV00/02.04.2012



EFFECTIS ERA AVRASYA TEST VE BELGELENDİRME A.Ş.

AB-0556-T

21.09.2015

RFTR15109

APPENDIXES:

Appendix A: Furnace and laboratory conditions

Appendix B: Test results

Appendix C: Photos



Bu rapor, laboratuvarın yazılı izni olmadan kısmen kopyalanıp çoğaltılamaz.
İmzasız ve mühürlü raporlar geçersizdir.

This report shall not be reproduced other than in full except with the permission of the laboratory. Testing reports without signature and seal are not valid

Phone: +902626581662

Fax.: +902626581669

E-mail: info@erayonetim.com
turkey@effectis.comWeb: www.erayonetim.com
www.effectis.com

FR1106/REV00/02.04.2012



Appendix A

EFFECTIS ERA AVRASYA TEST VE BELGELENDİRME A.Ş.

AB-0556-T

21.09.2015

RFTR15109



Bu rapor, laboratuvarın yazılı izni olmadan kısmen kopyalanıp çoğaltılamaz.
İmzasız ve mühürsüz raporlar geçersizdir.

This report shall not be reproduced other than in full except with the permission of the laboratory. Testing reports without signature and seal are not valid

Phone: +902626581662

Fax.: +902626581669

E-mail: info@erayonetim.com
turkey@efectis.comWeb: www.erayonetim.com
www.efectis.com

FR1106/REV00/02.04.2012

A-1/2



Appendix A

EFFECTIS ERA AVRASYA TEST VE BELGELENDİRME A.Ş.

AB-0556-T

21.09.2015

RFTR15109



Bu rapor, laboratuvarın yazılı izni olmadan kısmen kopyalanıp çoğaltılamaz.
İmzasız ve mühürsüz raporlar geçersizdir.

This report shall not be reproduced other than in full except with the permission of the laboratory. Testing reports without signature and seal are not valid

Phone: +902626581662

Fax.: +902626581669

E-mail: info@erayonetim.com
turkey@efectis.comWeb: www.erayonetim.com
www.efectis.com

FR1106/REV00/02.04.2012

A-2/2



Appendix B

EFFECTIS ERA AVRASYA TEST VE BELGELENDİRME A.Ş.

AB-0556-T

21.09.2015

RFTR15109

UNEXPOSED SIDE OF TEST FRAME




Figure B1: Locations of thermocouples and deflection sensors



Bu rapor, laboratuvarın yazılı izni olmadan kısmen kopyalanıp çoğaltılamaz.
İmzasız ve mühürsüz raporlar geçersizdir.

This report shall not be reproduced other than in full except with the permission of the laboratory. Testing reports without signature and seal are not valid

Phone: +902626581662

Fax.: +902626581669

E-mail: info@erayonetim.com
turkey@efectis.comWeb: www.erayonetim.com
www.efectis.com

FR1106/REV00/02.04.2012

B-1/5

Appendix B

EFFECTIS ERA AVRASYA TEST VE BELGELENDİRME A.Ş.

AB-0556-T

21.09.2015

RFTR15109




Figure B2: Surface temperatures (Thermocouple sensors for average temperature)



Bu rapor, laboratuvarın yazılı izni olmadan kısmen kopyalanıp çoğaltılamaz.
İmzasız ve mühürsüz raporlar geçersizdir.

This report shall not be reproduced other than in full except with the permission of the laboratory. Testing reports without signature and seal are not valid

Phone: +902626581662

Fax: +902626581669

E-mail: info@erayonetim.com
turkey@efectis.comWeb: www.erayonetim.com
www.efectis.com

FR1106/REV00/02.04.2012

B-2/5

Appendix B

EFFECTIS ERA AVRASYA TEST VE BELGELENDİRME A.Ş.

AB-0556-T

21.09.2015

RFTR15109




Figure B3: Surface temperatures (Thermocouple sensors for maximum temperature)



Bu rapor, laboratuvarın yazılı izni olmadan kısmen kopyalanıp çoğaltılamaz.
İmzasız ve mühürsüz raporlar geçersizdir.

This report shall not be reproduced other than in full except with the permission of the laboratory. Testing reports without signature and seal are not valid

Phone: +902626581662

Fax: +902626581669

E-mail: info@erayonetim.com
turkey@efectis.comWeb: www.erayonetim.com
www.efectis.com

FR1106/REV00/02.04.2012

B-3/5

Appendix B

EFFECTIS ERA AVRASYA TEST VE BELGELENDİRME A.Ş.

AB-0556-T

21.09.2015

RFTR15109




Figure B4: Deformation of the wall.



Bu rapor, laboratuvarın yazılı izni olmadan kısmen kopyalanıp çoğaltılamaz.
İmzasız ve mühürsüz raporlar geçersizdir.

This report shall not be reproduced other than in full except with the permission of the laboratory. Testing reports without signature and seal are not valid

Phone: +902626581662

Fax.: +902626581669

E-mail: info@erayonetim.com
turkey@efectis.comWeb: www.erayonetim.com
www.efectis.com

FR1106/REV00/02.04.2012

B-4/5

Appendix B

EFFECTIS ERA AVRASYA TEST VE BELGELENDİRME A.Ş.

AB-0556-T

21.09.2015

RFTR15109

Table B1: Data obtained from deformation sensors

Time (min)	Def. 1 (mm)	Def. 4 (mm)
0,0	0,00	0,00
2,0	0,38	4,10
4,0	2,75	7,38
6,0	2,78	7,38
8,0	2,78	8,28
10,0	2,78	17,48
12,0	9,10	31,15
14,0	17,90	40,38
16,0	23,83	45,70
18,0	27,33	49,63
20,0	31,55	55,85
22,0	36,08	64,68
24,0	46,28	75,28
26,0	56,65	86,78
28,0	67,15	97,68
30,0	76,35	105,10
32,0	83,28	109,95
34,0	89,45	113,33
36,0	94,13	115,83
38,0	97,43	117,53
40,0	100,45	117,88
42,0	102,38	117,90
44,0	103,85	117,80
46,0	105,43	116,58
48,0	107,70	115,60



Bu rapor, laboratuvarın yazılı izni olmadan kısmen kopyalanıp çoğaltılamaz.

İmzasız ve mühürsüz raporlar geçersizdir.

This report shall not be reproduced other than in full except with the permission of the laboratory. Testing reports without signature and seal are not valid

Phone: +902626581662

Fax.: +902626581669

E-mail: info@erayonetim.com
turkey@effectis.com

Web: www.erayonetim.com
www.effectis.com

FR1106/REV00/02.04.2012

B-5/5

Appendix C

EFFECTIS ERA AVRASYA TEST VE BELGELENDİRME A.Ş.

AB-0556-T

21.09.2015

RFTR15109




Photo C1: Unexposed side of the test specimen before the test



Bu rapor, laboratuvarın yazılı izni olmadan kısmen kopyalanıp çoğaltılamaz.
İmzasız ve mühürlü raporlar geçersizdir.

This report shall not be reproduced other than in full except with the permission of the laboratory. Testing reports without signature and seal are not valid

Phone: +902626581662

Fax: +902626581669

E-mail: info@erayonetim.com
turkey@effectis.comWeb: www.erayonetim.com
www.effectis.com

FR1106/REV00/02.04.2012

C-1/5

Appendix C

EFFECTIS ERA AVRASYA TEST VE BELGELENDİRME A.Ş.

AB-0556-T

21.09.2015

RFTR15109




Photo C2: Exposed side of the test specimen before the test

Bu rapor, laboratuvarın yazılı izni olmadan kısmen kopyalanıp çoğaltılamaz.
İmzasız ve mühürlü raporlar geçersizdir.

This report shall not be reproduced other than in full except with the permission of the laboratory. Testing reports without signature and seal are not valid

Phone: +902626581662

Fax.: +902626581669

E-mail: info@erayonetim.com
turkey@efectis.comWeb: www.erayonetim.com
www.efectis.com

FR1106/REV00/02.04.2012

C-2/5




Appendix C

EFFECTIS ERA AVRASYA TEST VE BELGELENDİRME A.Ş.

AB-0556-T

21.09.2015

RFTR15109

Photo C3: Unexposed side of the test specimen at 45th minute of the test

Bu rapor, laboratuvarın yazılı izni olmadan kısmen kopyalanıp çoğaltılamaz.
İmzasız ve mühürsüz raporlar geçersizdir.

This report shall not be reproduced other than in full except with the permission of the laboratory. Testing reports without signature and seal are not valid

Phone: +902626581662

Fax.: +902626581669

E-mail: info@erayonetim.com
turkey@efectis.comWeb: www.erayonetim.com
www.efectis.com

FR1106/REV00/02.04.2012

C-3/5



Appendix C

EFFECTIS ERA AVRASYA TEST VE BELGELENDİRME A.Ş.

AB-0556-T

21.09.2015

RFTR15109




Photo C4: Unexposed side of the test specimen after the test

Bu rapor, laboratuvarın yazılı izni olmadan kısmen kopyalanıp çoğaltılamaz.
İmzasız ve mühürsüz raporlar geçersizdir.

This report shall not be reproduced other than in full except with the permission of the laboratory. Testing reports without signature and seal are not valid

Phone: +902626581662

Fax.: +902626581669

E-mail: info@erayonetim.com
turkey@efectis.comWeb: www.erayonetim.com
www.efectis.com

FR1106/REV00/02.04.2012

C-4/5



Appendix C

EFFECTIS ERA AVRASYA TEST VE BELGELENDİRME A.Ş.

AB-0556-T

21.09.2015

RFTR15109



Photo C5: Exposed side of the test specimen after the test

Bu rapor, laboratuvarın yazılı izni olmadan kısmen kopyalanıp çoğaltılamaz.
İmzasız ve mühürsüz raporlar geçersizdir.

This report shall not be reproduced other than in full except with the permission of the laboratory. Testing reports without signature and seal are not valid

Phone: +902626581662

Fax.: +902626581669

E-mail: info@erayonetim.com
turkey@efectis.comWeb: www.erayonetim.com
www.efectis.com

FR1106/REV00/02.04.2012

C-5/5

