



TÜRKAK - TÜRK AKREDİTASYON KURUMU tarafından akredite  
Accredited by TÜRKAK  
**TSE DENEY ve KALİBRASYON MERKEZİ BAŞKANLIĞI**  
Elektroteknik ve Kimya Laboratuvarları Grup Başkanlığı  
Ege Bölge Laboratuvarları Müdürlüğü

Adres: 8780/1 sokak No:5 Çigli/IZMİR  
Tel: +90 (232) 376 24 25 Fax: +90 (232) 386 15 10 E-posta: egebolgelab@tse.org.tr Web: www.tse.org.tr



AB-0001-T
256515
05-15

HEADSHIP OF TSE TEST and CALIBRATION CENTER  
AEGEAN REGIONAL LABORATORIES (IZMIR)

Address: 8780/1 sokak No:5 Çigli/IZMİR  
Tel: +90 (232) 376 24 25 Fax: +90 (232) 386 15 10 E-mail: egebolgelab@tse.org.tr Web: www.tse.org.tr

**MUAYENE VE DENEY RAPORU**  
**TEST REPORT**

<b>Deneyi Talep Eden</b> (Adı, Adresi, Şehir vb.)	: NEV PANEL YAPI MADEN ÜR.İTH.İHR.SAN.VE TİC.LTD.ŞTİ.
<i>Customer (Name,Address,City etc.)</i>	BAĞDAT CAD.ÇOLAKOĞLU İŞ MERKEZİ No:458/30 Maltepe-İSTANBUL
<b>Deney Talep Tarihi/No</b> <i>Order Date / No</i>	: 17.04.2015 / 127830
<b>Numunenin Tanımı</b> (Cins, Marka, Tip, Tür, Model vb.)	: YAPI PANELİ, , , -, 1.00 adet
<i>Sample Description(Type,Mark,Model etc.)</i>	BUILDING PANEL..., 1,00 item
<b>Numune Kabul Tarihi</b> <i>Test Item Receipt Date</i>	: 17.04.2015
<b>Deneylerin Yapıldığı Tarih</b> <i>Date of Test</i>	: 17.04.2015 - 20.05.2015
<b>Uygulanan Standard / Metod</b> <i>Applied Standard/Method</i>	: TS EN ISO 8990:2002-01 Isı Yalıtımı- Kararlı Durum Isı İletim Özelliklerinin Tayini- Kalibre Edilmiş ve Mahfazalı Sıcak Kutu TS EN ISO 8990:2002-01 Thermal insulation-Determination of steady-State thermal transmission properties-Calibrated and guarded hot boxx
<b>Raporun Sayfa Sayısı</b> <i>Number of pages of the report</i>	: 2
<b>Açıklamalar</b> <i>Remarks</i>	:

Türk Akreditasyon Kurumu(TÜRKAK) deney raporlarının tanınması konusunda Avrupa Akreditasyon Birliği(EA) ve Uluslararası Laboratuvar Akreditasyon Birliği(ILAC) ile karşılıklı tanınma anlaşmasını imzalamıştır.

The Turkish Accreditation Agency(TURKAK) is signatory to the multilateral agreements of the European co-operation for the Accreditation(EA) and of the International Laboratory Accreditation(ILAC) for the Mutual recognition of test reports.

Deney ve/veya ölçüm sonuçları, genişletilmiş ölçüm belirsizlikleri (olması halinde), ve deney metodları bu raporun tamamlayıcı kismı olan takip eden sayfalarda verilmiştir.

The test and/or measurement results, the uncertainties (if applicable) with confidence probability and test methods are given on the following pages which are part of this report.

Bu rapor özel deney talebine istinaden düzenlenmiş olup, Standartlara Uygunluk Belgesi niteliğinde değildir. Partiyi temsil etmez, ayrıca ilan, reklam ve ihalelerde uygunluk belgesi niteliğinde kullanılamaz.

This test report was prepared upon customer's request, can not be used as certificate of conformity to standards, does not represent a batch and can not be used as conformity document for advertisements and procurements .



**Deney Sorumlusu**  
Person in charge of tests

Akide Selcen HERGÜN  
Tekniker

**Kontrol Eden**  
Reviewer

Murat GÜR  
Teknik Şef

**Onaylayan**  
Approved by

Murat GÜR  
Teknik Şef

Bu rapor, hazırlayan laboratuvarın yazılı izni olmadan kısmen kopyalanıp çoğaltılmaz. İmzasız ve mühürsüz raporlar geçersizdir.

Bu rapor, sadece deney yapılmış numune için geçerlidir ve "Ürün Belgesi" yerine geçmez.

This test report shall not be reproduced other than in full except with the written permission of the laboratory. Test reports without signature and seal are not valid.

This test report represents only tested sample(s), and shall not be used as Product Certificate

FATURADA 16.05.2015

**MAGHOR, s.r.o.**  
Košická 2  
045 01 Moldava nad Bodvou

**İČO** 53601963  
**DIČ** SK2121484156 (VAT nr.)  
**IBAN** SK10 1100 0000 0029 4410 0286



TSE DENEY ve KALİBRASYON MERKEZİ BAŞKANLIĞI TÜRGUTLU YAPI MAZLEMELERİ  
LABORATUVARI  
HEADSHIP OF TSE TEST AND CALIBRATION CENTER TURGUTLU CONSTRUCTION MATERIALS  
LABORATORY

256515/05.15  
AB-0001-T

MUAYENE - DENEY SONUÇLARI TEST RESULTS

(*)Standardda Requested	Contained In The	The Result																																				
5.6 Thermal behavior characteristics  TS EN ISO 8990 TS EN 1745	<p><b>Stated dimensions (70)mm.</b> Profile system + mgo panel + ceramic wool and screw constructed with</p> <p>According to TS EN 1745 Standard test methods (TS EN ISO 8990) experiment is performed, measured and calculated the thermal transmission properties are given below.</p> <table border="1"> <tr> <td>Test equipment:</td> <td>Measuring area 1 m<sup>2</sup>, the hot box</td> </tr> <tr> <td>Test sample:</td> <td>1 m<sup>2</sup> of wall.</td> </tr> <tr> <td>Algılayıcıların presentation along with the location</td> <td>Hot surface in 9 nine of cold surface probe, probe</td> </tr> <tr> <td>The conditioning process sample experiments:</td> <td>23 ° c ± 2 temperature and relative humidity of 50% ± 5 are conditioned.</td> </tr> <tr> <td>Test specimen according to the format:</td> <td>Vertical</td> </tr> <tr> <td>Heat flow direction:</td> <td>Horizontal</td> </tr> <tr> <td>The intensity of the heat flow rate: q (W/m<sup>2</sup>)</td> <td>22,287</td> </tr> <tr> <td>The hot air temperature: (° c)</td> <td>24,86</td> </tr> <tr> <td>Cold side air temperature (° c)</td> <td>-4,93</td> </tr> <tr> <td>Hot-side surface temperature (° c)</td> <td>24,37</td> </tr> <tr> <td>Cold-side surface temperature (° c)</td> <td>-4,78</td> </tr> <tr> <td>Measured thermal resistance: R (m<sup>2</sup>k/W)</td> <td>1,167</td> </tr> <tr> <td>R<sub>si</sub> (m<sup>2</sup>K/W):</td> <td>0,13</td> </tr> <tr> <td>R<sub>se</sub> (m<sup>2</sup>K/W):</td> <td>0,04</td> </tr> <tr> <td>R<sub>T</sub> (m<sup>2</sup>K/W)= R+ R<sub>si</sub> + R<sub>se</sub></td> <td>1,337</td> </tr> <tr> <td>U (W /m<sup>2</sup>K)= 1/R<sub>T</sub> :</td> <td>0,748</td> </tr> <tr> <td>The estimated accuracy:</td> <td>5%</td> </tr> <tr> <td>Experimental period:</td> <td>3 day</td> </tr> </table> <p>(λ = d/R) belongs to the above specimen from his relationship λ = 0,060 W/mK are calculated as.</p>	Test equipment:	Measuring area 1 m <sup>2</sup> , the hot box	Test sample:	1 m <sup>2</sup> of wall.	Algılayıcıların presentation along with the location	Hot surface in 9 nine of cold surface probe, probe	The conditioning process sample experiments:	23 ° c ± 2 temperature and relative humidity of 50% ± 5 are conditioned.	Test specimen according to the format:	Vertical	Heat flow direction:	Horizontal	The intensity of the heat flow rate: q (W/m <sup>2</sup> )	22,287	The hot air temperature: (° c)	24,86	Cold side air temperature (° c)	-4,93	Hot-side surface temperature (° c)	24,37	Cold-side surface temperature (° c)	-4,78	Measured thermal resistance: R (m <sup>2</sup> k/W)	1,167	R <sub>si</sub> (m <sup>2</sup> K/W):	0,13	R <sub>se</sub> (m <sup>2</sup> K/W):	0,04	R <sub>T</sub> (m <sup>2</sup> K/W)= R+ R <sub>si</sub> + R <sub>se</sub>	1,337	U (W /m <sup>2</sup> K)= 1/R <sub>T</sub> :	0,748	The estimated accuracy:	5%	Experimental period:	3 day	
Test equipment:	Measuring area 1 m <sup>2</sup> , the hot box																																					
Test sample:	1 m <sup>2</sup> of wall.																																					
Algılayıcıların presentation along with the location	Hot surface in 9 nine of cold surface probe, probe																																					
The conditioning process sample experiments:	23 ° c ± 2 temperature and relative humidity of 50% ± 5 are conditioned.																																					
Test specimen according to the format:	Vertical																																					
Heat flow direction:	Horizontal																																					
The intensity of the heat flow rate: q (W/m <sup>2</sup> )	22,287																																					
The hot air temperature: (° c)	24,86																																					
Cold side air temperature (° c)	-4,93																																					
Hot-side surface temperature (° c)	24,37																																					
Cold-side surface temperature (° c)	-4,78																																					
Measured thermal resistance: R (m <sup>2</sup> k/W)	1,167																																					
R <sub>si</sub> (m <sup>2</sup> K/W):	0,13																																					
R <sub>se</sub> (m <sup>2</sup> K/W):	0,04																																					
R <sub>T</sub> (m <sup>2</sup> K/W)= R+ R <sub>si</sub> + R <sub>se</sub>	1,337																																					
U (W /m <sup>2</sup> K)= 1/R <sub>T</sub> :	0,748																																					
The estimated accuracy:	5%																																					
Experimental period:	3 day																																					

\* ACCREDITATION REASSURANCE



2/2

LAB-D-FR-36/15.08.2014-0

The estimated accuracy: